

























TECNICAL CHARACTERISTICS

wineo 600 Rigid

Heterogeneous resilient-flooring for glueless installation - Covering type according to DIN EN 16511

wineo

	wood	wood XL	stone XL	
				
Format	1212 x 186 mm	1507 x 234 mm	746 x 477 mm	
Product thickness	5 mm	5 mm	5 mm	
Planks, tiles / m² per box	8 / 1.80 m ²	6 / 2.12 m ²	6 / 2.14 m ²	
Boxes / m² per pallet	56 / 100.80 m ²	48 / 101.76 m ²	44 / 94.16 m ²	
Guarantee Extended warranty	20 years for private use according to Windmüller warranty conditions - www.wineo.de + 5 years for laying on PU underlay mat			
Classification				Product composition
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage		1 Surface seal
	Utilization class 32 EN ISO 10874	Commercial sector with average usage		2 Surface texture Various embossings
	Wear layer binder content EN ISO 10582	Typ I		3 Wear layer Thickness 0.4 mm
	R9 Anti slip category DIN 51130	R 9		4 Design Decor film
	Resistance to staining EN 438-2	Group 1 + 2: grade 5 Group 3: grade 4		5 Elastic top layer
	Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6		6 Core board
	Residual indentation EN ISO 24343-1	≤ 0.1 mm		7 Profile connection Connect technology 
	Thermal resistance EN 12667	~ 0.05 (m ² K)/W without underlay mat ~ 0.06 (m ² K)/W with silentRIGID		8 Elastic bottom layer
	Castor chair test ISO 4918	25000 revolutions no damage with rolls type W		9 Underlay material silentRIGID (available separately)
	Anti-static properties EN 1815	≤ 2 kV		wood - Bevelled edge wood XL - registered embossed surface - Bevelled edge stone XL - real joint
	Impact sound reduction EN ISO 16251-1	~ 6 dB without underlay mat up to 13 dB with silentRIGID		
	Dimensional stability EN ISO 23999	~ 0.1 %		
	REACH	free from SVHC substances ≥ 0.1 %		
	Disposal	Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203		
<div style="display: flex; justify-content: space-between; align-items: flex-start;"> <div style="border: 1px solid black; padding: 5px; width: 30%;">  <p>Windmüller GmbH Nord-West-Ring 21 D-32832 Augustdorf</p> <p>DOP: 0301012 EN 14041:2004 / AC2006 1658</p> <div style="display: flex; justify-content: space-around;">      </div> <p>www.wineo.de</p> </div> <div style="width: 30%; text-align: center;">  <p>ÉMISSIONS DANS L'AIR INTÉRIEUR*</p> <p>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</p> </div> <div style="width: 30%; text-align: center;">  <p>70 710 4061-4 www.profi-cert.com</p> <p>PREMIUM</p> <p>emissionsgeprüft schadstoffgeprüft</p> </div> <div style="width: 30%; text-align: center;">  <p>Phthalate frei</p>  <p>factory made coated</p> </div> </div>				

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.