
TECNICAL CHARACTERISTICS

wineo 600 Rigid

Heterogeneous resilient-flooring for glueless installation - Covering type according to DIN EN 16511

wineo

	wood	wood XL	stone XL
Format	1212 x 186 mm	1507 x 234 mm	746 x 477 mm
Product thickness	5 mm	5 mm	5 mm
Planks, tiles / m² per box	8 / 1.80 m²	6 / 2.12 m²	6 / 2.14 m²
Boxes / m² per pallet	56 / 100.80 m²	48 / 101.76 m²	44 / 94.16 m²
Guarantee	You can find our guarantee conditions at - www.wineo.de		



Classification		Product composition	
Utilization class 23 EN ISO 10874	Domestic area with intensive usage	1	**Surface seal**
Utilization class 32 EN ISO 10874	Commercial sector with average usage	2	**Surface texture** Various embossings
Wear layer binder content EN ISO 10582	Typ I	3	**Wear layer** Thickness 0.4 mm
Anti slip category DIN 51130	R 9	4	**Design** Decor film
Resistance to staining EN 438-2	Group 1 + 2: grade 5 Group 3: grade 4	5	**Elastic top layer**
Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6	6	**Core board**
Residual indentation EN ISO 24343-1	≤ 0.1 mm	7	**Profile connection** Connect technology
Thermal resistance EN 12667	~ 0.05 (m²K)/W without underlay mat ~ 0.06 (m²K)/W with silentRIGID	8	**Elastic bottom layer**
Castor chair test ISO 4918	25000 revolutions no damage with rolls type W	9	**Underlay material silentRIGID** (available separately)
Anti-static properties EN 1815	≤ 2 kV		wood - Bevelled edge wood XL - registered embossed surface - Bevelled edge stone XL - real joint
Impact sound reduction EN ISO 16251-1	~ 6 dB without underlay mat up to 13 dB with silentRIGID		
Dimensional stability EN ISO 23999	≤ 0,1%		
REACH	free from SVHC substances ≥ 0.1 %		
Disposal	Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203		

CE - 25 -
Windmöller GmbH
Charles-Lindbergh-Ring 13
D-32756 Detmold
DOP: 0301012
EN 14041:2004 / AC2006
1658
Bfl-s1 DS E1 HCHO
www.wineo.de

ÉMISSIONS DANS L'AIR INTÉRIEUR
A+ A B C
Information representative des emissions dans l'air interieur des substances volatiles presentant un risque de toxicite par inhalation, sur une echelle de classe allant de C (fortes emissions) a A+ (tres faibles emissions)

Phthalat frei · Phthalate free

factorymade coated

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmöller GmbH.