
TECHNICAL CHARACTERISTICS

wineo 600

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

	wineo 600 wood	wineo 600 wood XL	wineo 600 stone XL
Format	1200 x 180 mm	1505 x 235 mm	914 x 457 mm
Product thickness	2 mm	2 mm	2 mm
Planks, tiles / m² per box	18 / 3.89 m²	12 / 4.24 m²	12 / 5.01 m²
Boxes / m² per pallet	60 / 233.40 m²	64 / 271.36 m²	52 / 260.52 m²
Guarantee	You can find our guarantee conditions at - www.wineo.de		



Classification

Utilization class 23 EN ISO 10874	Domestic area with intensive usage
Utilization class 32 EN ISO 10874	Commercial sector with average usage
Utilization class 41 EN ISO 10874	Light industry sector with moderate usage
Wear layer binder content EN ISO 10582	Typ I
Anti slip category DIN 51130	R 9
Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time
Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6
Residual indentation EN ISO 24343-1	≤ 0,1 mm without underlay mat ~ 0.17 mm with silentPREMIUM
Castor chair test ISO 4918	25000 revolutions no damage with rolls type W
Thermal resistance EN 12667	≤ 0.011 (m²K)/W without underlay mat ≤ 0.021 (m²K)/W with silentPREMIUM or silentPLUS
Impact sound reduction EN ISO 16251-1	~ 4 dB ~ 17 dB with silentPLUS
Dimensional stability EN ISO 23999	≤ 0,15 %
REACH	free from SVHC substances ≥ 0.1 %
Disposal	Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203

Product composition

1	**Surface seal**
2	**Surface texture** Various embossings
3	**Wear layer** Thickness 0.4 mm
4	**Design** Decor film
5	**Base layer**
6	**Backing**
7	**Underlay material silentPLUS** (available separately)

TÜV PROFI CERT product 70 710 4061-4 www.proficert.com

TFI emissionsgeprüft schadstoffgeprüft PREMIUM

CE - 25 -

Windmöller GmbH
Charles-Lindbergh-Ring 13
D-32756 Detmold

DOP: 0301010
EN 14041:2004 / AC2006
1658

Bfl-s1 | DS | E1 HCHO | ≤ 2 kV | ≥ 0,15 W/(mK)

www.wineo.de

ÉMISSIONS DANS L'AIR INTÉRIEUR* A+ (A+ A B C)

Information representative des emissions dans l'air interieur des substances volatiles presentant un risque de toxicite par inhalation, sur une echelle de classe allant de C (fortes emissions) a A+ (tres faibles emissions)

Phthalat frei / Phthalate free

factory made coated

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 29° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmöller GmbH.