TECHNICAL CHARACTERISTICS

wineo 800 to glue - 2025

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

	wood L	wood XL	stone XL
Format	1200 x 180 mm	1505 x 235 mm	914 x 457 mm
Product thickness	2,5 mm	2,5 mm	2,5 mm
Weight	4,4 kg/m²	4,4 kg/m²	4,4 kg/m²
Planks / m² per box	16 / 3,46 m²	12 / 4,24 m²	8 / 3,34 m²
Boxes / m² per pallet	60 / 207,60 m²	52 / 220,48 m²	64 / 213,76 m²
Guarantee	You can find our guarantee conditions at – www.wineo.de		



Classification		
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage
	Utilization class 33 EN ISO 10874	Commercial sector with heavy usage
	Utilization class 42 EN ISO 10874	Light industry sector with regular usage
	Wear layer binder content EN ISO 10582	Typ I
R10	Anti slip category DIN 51130	R 10
	Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time
	Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6
	Residual indentation EN ISO 24343-1	≤ 0,1 mm without underlay mat ~ 0,17 mm with singleGLUE or doubleGLUE ~ 0,2 mm with silentPLUS
	Castor chair test ISO 4918	25000 revolutions no damage with rolls type W
	Thermal resistance EN 12667	≤ 0,012 (m²K)/W without underlay mat ≤ 0,022 (m²K)/W with singleGLUE or doubleGLUE ≤ 0,026 (m²K)/W with silentPLUS
	Impact sound reduction EN ISO 16251-1	~ 5 dB without underlay mat ~ 10 dB with singleGLUE or doubleGLUE ~ 15 dB with silentPLUS
	Dimensional stability EN ISO 23999	≤ 0,15 %
	REACH	free from SVHC substances ≥ 0,1 %
	Disposal	Private: Possible with normal domestic refuse Commercial: Refuse-key-no. AVV 170203

Product composition	
1	**Cover element** Surface structure Surface sealing Wear layer and decorative film
2	**Base layer**
3	**Backing**
	micro bevel

CE
Windmöller GmbH
Charles-Lindbergh-Ring 13
D-32756 Detmold
- 25 -
DOP: 0301010
EN 14041:2004 / AC2006
1658
Bfl-s1 DS E1 HCHO ≤ 2 kV ≥ 0,15 W/(mK)
www.wineo.de

ÉMISSIONS DANS L'AIR INTÉRIEUR*
A+
A+ A B C
Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)

TÜV PROFI CERT product
70 710 4061-3
www.proficert.com
TÜV Hessen
TÜV emissionsgeprüft schadstoffgeprüft
PREMIUM

Phthalat frei – Phthalate free

factorymade coated

Relevant information:

- Utilization class 42 is not possible in conjunction with singleGLUE, doubleGLUE or silentPLUS.
- Underfloor heating
  Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 29° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmöller GmbH.