

TECHNICAL CHARACTERISTICS

PURLINE wineo 1500 plank+tile plank to glue							wineo	
Permanently elastic polyurethane flooring according to EN 16776 Without the addition of chlorine, without plasticizers or solvents.								
	wood XS	wood L	wood XL	stone XL	graphic XL textile XL	fusion XL		
Format	480x80 mm	1200x200 mm	1500x250 mm	1000x500 mm	1000x500 mm	1000x500 mm		
Product thickness	2,5 mm	2,5 mm	2,5 mm	2,5 mm	2,5 mm	2,5 mm		
Weight	3,4 kg/m²	3,4 kg/m²	3,4 kg/m²	3,4 kg/m²	3,4 kg/m²	3,4 kg/m²		
Planks / m² per box	40 / 1,54 m²	20 / 4,80 m²	12 / 4,50 m²	10 / 5,00 m²	10 / 5,00 m²	10 / 5,00 m²		
Boxes / m² per pallet	144/221,76 m²	60/288,00 m²	56/252,00 m²	54/270,00 m²	54/270,00 m²	50/250,00 m²		
Guarantee	You can find our guarantee conditions at – www.wineo.de							
Classification							Product composition	
	Utilization class 23 EN ISO 10874			Domestic area with intensive usage			1	Top element • PU-top layer with surface structure • decor paper • stabilisation
	Utilization class 34 EN ISO 10874			Commercial sector with intensive usage				
	Utilization class 43 EN ISO 10874			Light industry sector with heavy usage				
Scratch resistance EN 16776, annex A				Utilization class 34 ≥ 6 N Utilization class 43 ≥ 7 N			2	Base layer high performance composite material
Anti slip category bfu R 9729				GS 1 / GS 2 structure-dependent				
	R9	Anti slip category DIN 51130		R9			3	Backing Integrated Fleece TEC-System
	Staining and chemical resistance EN ISO 26987			Very good resistance according to the concentration and residence time				
	Light fastness EN ISO 105-B02			~ 7				
	Residual indentation EN ISO 24343-1			≤ 0.10 mm				
	Effect of a furniture leg EN 424			Foot type 2 – no visible change				
	Castor chair test ISO 4918			25000 revolutions no damage with rolls type W				
	Thermal resistance ISO 8302			~ 0.01 (m²K)/W				
	Impact sound reduction EN ISO 10140			~ 8 dB				
	Dimension stability EN ISO 23999			≤ 0,15 %				
	Flexural behaviour EN ISO 24344			≥ 20 mm				
REACH				free from SVHC substances ≥ 0.1 %				
Disposal				<u>Private:</u> possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203				
Relevant Information: • Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperatur of 29 °C. • Cleaning and care: See separate cleaning & care instruction. • Technical subjects can be changed by Windmüller GmbH.								